



Taraflex® Surface

	Standard	Requirement	Unit	Result	Tolerance	
DESCRIPTION						
Surface treatment	-	-	-	Triple Action Protecsol®		
Surface complex	-	-	-	D-Max™		
Foam backing	-	-	-	-		
Anti-bacterial & Fungicidal treatment			-			
Thickness	-	EN 428	-	mm	2.1	± 0.10
	-	-	-	inch	0.08''	± 0.012
Weight	-	EN 430	-	kg/m ²	2.9	± 0.15
	-	-	-	lbs/sq ft	0.59	± 0.03
Length	-	EN 426	-	lm	30 MAX	-0 / +0.20
	-	-	-	linear ft	98'5'' MAX	-0 / +0.06
Width	-	EN 426	-	lm	1.5	-0 / +0.01
	-	-	-	linear ft	4'11''	-0 / +0.03
SPORT PROPERTIES						
Shock absorption	CEN	EN 14808	≥ 25	%		
	DIN	DIN 18032	> 50	%		
Vertical deformation	CEN	EN 14809	≤ 3.5	mm		
	DIN	DIN 18032	≤ 3.5	mm		
Energy return	Fr.	NF P 90 203	≥ 0.31	m/s		
Sliding coefficient	CEN	EN 13036-4	80-110	-	80-110	
	DIN	DIN 18032	0.4-0.6	-	0.4-0.6	
Ball bounce	CEN	EN 12235	≥ 90	%	≥ 90	
	DIN	DIN 18032	≥ 90	%	≥ 90	
TECHNICAL CHARACTERISTICS						
Indentation resistance	CEN	EN 1516	≤ 0.5	mm	≤ 0.5	
Static load limit	USA	ASTM F 970	≤ 0.005	inch		
Abrasion resistance	CEN	EN ISO 5470-1	≤ 1000	mg	≤ 350	
Impact resistance	CEN	EN 1517	≥ 8	N.m	≥ 8	
Rolling load resistance	CEN	EN 1569	≥ 1500	N	≥ 1500	
	DIN	DIN 18032	≥ 1000	N	≥ 1000	
Brightness	CEN	ISO 2813	≤ 30	%	≤ 30	
Sound Insulation	CEN	EN ISO 717-2	-	dB	3	
CLASSIFICATION						
Fire	USA	ASTM E 648	-		Class 1	
Chemical resistance	USA	ASTM D 543	-	-	OK	