

**DESCRIPTION**

Total thickness	ASTM F386-02	inch	0.24
	EN 428	mm	6.00
Thickness of wearlayer	ASTM F410-02	inch	0.03
	EN 429	mm	0.70
Weight	-	lbs/sq.ft.	2.03
	EN 430	g/sq.m	9895
Plank size	ASTM F 536	inch	6.929" x 39.37"
	EN 427	mm	176 x 1000
Coverage / box	-	sq.ft.	17.2
	-	sq.m	1.4

**CLASSIFICATION**

Reference specification	ASTM F 1700- 04	-	Class III Type B
Fire rating	ASTM E648-08	class	Class 1
	CAN/ULC S102.2	-	-

**PERFORMANCE**

Anti-bacterial and fungicidal treatment	-	-	OK
Surface treatment	-	-	PUR+
Abrasion	<b>ASTM F510-04</b>	mg	1.1
Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2
	<b>ASTM D2047-04</b>	-	0.9
Coefficient of friction	<b>ASTM C1028-96</b>		0.73
	<b>ASTM F970-00</b>	inch	0.004
Static load (250 psi)			
Dimensional stability	EN 434	%	≤ 0.15
Impact insulation class	<b>ASTM E989-06</b>	-	47
Thermal conductivity	EN 12524	W/(m.K)	0.25
Chemical & stain resistance	<b>ASTM F925-02</b>	-	Excellent Test results available upon request

**ENVIRONMENT**

Certification	-	-	Floorscore™
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100