






| DESCRIPTION | | | |
|--|----------------------------|--------------------|---|
| Total thickness | EN ISO 24346 [EN 428] | mm | 6.00 |
| Thickness of wearlayer | EN ISO 24340 [EN 429] | mm | 2 |
| Weight | EN ISO 23997 [EN 430] | g/m ² | 9365 |
| Tile size | EN ISO 24342 [EN 427] | mm | 635 x 635 GTI Connect |
| | | | 600 x 600 GTI Cleantech (without dovetail) (1) |
| CLASSIFICATION | | | |
| Norm / Product specification | - | - | EN ISO 10582 [EN 649] |
| European classification | EN ISO 10874 (EN 685) | class | 34 - 43 |
| Fire rating | EN 13 501-1 | class | B _{f1} -s1 |
| Static electrical propensity | EN 1815 | kV | < 2 |
| Slip resistance wet: ramp test with oil | DIN 51130 | class | R10 |
| Pendulum test | BS7976 | - | HSE 36 compliant Béton emboss References : Ermellino – Ora – Bora – Libeccio – Grecale – Scirocco – Tramontana |
| | | | NO Rice emboss References : Red – Blue – Green – Yellow – Black – Light Grey – Dark Grey – Carbon – Magma – Saphir – Aluminium – Titanium – Peler – Levente – Ponente – Maestrale |
| PERFORMANCE | | | |
| Wear resistance | EN 660.2 | mm ³ | ≤ 2 |
| Wear group | NF 189 | group | T |
| Type Binder content | EN ISO 10582 | type | I |
| Dimensional stability | EN ISO 23999 [EN 434] | % | ≤ 0.15 |
| Residual indentation | EN ISO 24343-1 [EN 433] | | ≤ 0.10 |
| Castor chair test (type W) | ISO 4918 (EN 425) | - | OK |
| Shore hardness | EN ISO 868 | H _D | ≥ 55 |
| Shifting resistance | CAHIER CSTB 3562 | N/mm ² | ≥ 30 |
| Thermal conductivity | EN ISO 10456 (EN12524) | W/(m.K) | 0.25 |
| Colour fastness | EN 20 105 - B02 | degree | ≥ 6 |
| Surface treatment | - | - | PUR+ |
| Chemical products resistance | EN ISO 26987 [EN 423] | - | OK |
| ENVIRONMENT / INDOOR AIR QUALITY | | | |
| TVOC after 28 days | ISO 16000-6 | µg/ m ³ | < 100 |
| Certification | - | - | Floorscore® |
| CE MARKING | | | |
|  | EN 14041 | - |    |
| | | - |  |

(1) Available upon request